

<Dimer acid & Trimer acid>

Product name	Typical properties				Typical composition			Packing		
	Color Gardner	Acid Value mg KOH / g	Saponification Value mg KOH / g	Viscosity mPa·s (25°C)	Monomer Acid GC%	Dimer acid GC%	Trimer acid GC%	Can	Drum	ISO-tank
Tsunodyme 205	6-7	194	198	6,200	4	86	10	-	●	●
Tsunodyme 216	7-	194	198	6,800	3	86	11	●	●	●
Tsunodyme 228	7-8	195	199	8,500	1	87	12	●	●	●
Tsunodyme 205(W)	5+	193	198	5,400	4	86	10	-	●	●
Tsunodyme 216(W)	5-6	193	198	6,700	3	86	11	●	●	●
Tsunodyme 228(W)	6-	193	199	8,100	1	87	12	●	●	●
Tsunodyme 395	3	195	199	6,000	1	97	2	●	●	-
Tsunodyme 346	11	182	199	36,000	1	34	65	-	●	-

Typical properties and typical compositions are not guaranteed the values of each products.