

★Curing agent for epoxy resin

Product name	Typical Properties						Packing		Main application	Characteristic
	Amine Value KOHmg/g	Viscosity mPa·s (25°C)	Viscosity mPa·s (75°C)	Resin content %	Flash Point °C	Appearance	Can	Drum		
							-	●		
Vegechem Green V115	230-246		3,500	100	>250	Yellowish-brown liquid	-	●	Paint·Adhesive	Flexible
Vegechem Green V125	330-360		800	100	215	Yellowish-brown liquid	-	●	Paint·Adhesive	Flexible
Vegechem Green V140	370-400		450	100	204	Yellowish-brown liquid	-	●	Paint·Adhesive	Flexible
Vegechem Green V1460	560-620	5,000		100	180	Yellowish-brown liquid	-	●	Adhesive	High heat resistance·High elastic modulus
Vegechem Green G152	435-455	300		100	200	Yellowish-brown liquid	-	●	Paint	Low viscosity·Good anti moisture curability
Vegechem Green G250	425-450	700		100	230	Yellowish-brown liquid	-	●	Adhesive·Coated Flooring	Low viscosity
Vegechem Green G747	450-475	300		100	230	Yellowish-brown liquid	-	●	Civil work·Injections agent	Low viscosity·Low calorific value
Vegechem Green V100XB65	54-63	2,500		65	31	Yellowish-brown liquid	-	●	Paint	Long working life·Flexible
Vegechem Green V1020	65-85	4,500		65	31	Yellowish-brown liquid	-	●	Paint	Long working life·Flexible
Vegechem Green V115M70	160-180	350		70	13	Yellowish-brown liquid	-	●	Paint·Adhesive	Good for Water resistance/Corrosion resistance, Tolene/Xylene free
Vegechem Green V115X70	161-173	900		70	27	Yellowish-brown liquid	-	●	Paint	Good for Water resistance/Corrosion resistance
Vegechem Green V230XB60	115-130	2,300		60	26	Yellowish-brown liquid	-	●	Paint	Good for compatibility to Epoxy resin·Water/Salt water resistant
Vegechem Green V260	56-67	4,500		65	28	Yellowish-brown liquid	-	●	Paint	Good for compatibility to Epoxy resin·Long working life
Vegechem Green V280X75	240-260	2,500		75	39	Yellowish-brown liquid	-	●	Paint	Good for compatibility to Epoxy resin·Long working life
Vegechem Green V2102	120-150	3,000		70	28	Yellowish-brown liquid	-	●	Paint	Flexible·Good for weatherability