

< Ester >

Product name	Typical properties								Packing		
	Color Gardner	Acid value mg KOH / g	Hydroxy value mg KOH / g	Saponification Value mg KOH / g	Iodine Value g I2/100 g	Kinematic viscosity(40°C) mm ² / s	Pour point °C	Flash point °C	Can	Drum	ISO tank
TFE-120SB	5	6.2	204	151	90	240	-10.0	256	-	●	●
TFE-4113B	1	0.8	0.7	144	67	11	-27.5	214	-	●	
TFE-EHPS	1-	0.3	0.1	149	0.6	9	2.5	212	-	●	●
TFE-45EH	1-	0.2	0.5	142	48	12	-15.0	216	-	●	
TFE-47TM	5	2.5	37	141	62	78	-10.0	220	-	●	
TFE-ME	8	0.3	-	190	112	5	-7.5	170	-	●	●
TFE-MED	1-	0.2	-	192	111	4	-5.0	175	-	●	●
TFE-OLNP-M	1-	0.4	5.9	203	47	20	-15.0	266	-	●	
TFE-OLPG	1-	0.2	8.1	187	85	20	-22.5	265	-	●	
TFE-RDDG	8-	87.0	0.3	186	112	2,927	5.0	281	-	●	
TFE-SREH	1-	0.1	1.3	144	88	8	-27.5	214	-	●	
TFE-SRNB	3	0.7	-	164	104	6	-12.5	205	-	●	

Typical properties and typical compositions are not guaranteed the values of each products.